



DEPARTMENT OF SCIENCE SERVICE  
 RAMA VI ROAD, RATCHATHEWI DISTRICT  
 BANGKOK 10400, THAILAND

No. 0307/ 3524

MAHAPHANT FIBRE CEMENT PUBLIC COMPANY LIMITED  
 59 Moo 12 Saraburi - Lomsak Rd.,  
 Chongsarika Dist, Pattananikhom  
 Lopburi 15220

16

March 2005

Dear Sirs,

With reference to your request of 28 February 2005, Ref. No.1421,  
 we are pleased to send you the following report on the sample/s of "FC BOARD, FC BOARD ( 20-)"  
 received on 28 February 2005.

Yours truly,

*Tida Kerdkumral*  
 (Ms. Tida Kerdkumral)


Physics and Engineering Program  
 Tel. 0 2201 7130


Director, Physics and Engineering Program

REPORT

Sender's Sample Designation	Marking	Laboratory No.	Thermal conductivity (W/m.K)
FC BOARD	-	XU.937	0.077
FC BOARD ( 20 ) Ca(O <sub>3</sub> 30% -	-	XU.938	0.150 ✓

Sample Description : Square sheet  
 Tested Date : 8 - 9 March 2005  
 Test Method : ASTM C-177

Approved by  
  
 (Mr. Sun Jhitkraisakorn)  
 Scientist 8

Reported by  
  
 (Mr. Puckanai Thongthiumporn)  
 Scientist 8

The above report is valid for the received sample/s only. The report does not guarantee any such material of the same brand or marking which may be sold in the market  
**THIS REPORT IS NOT TO BE USED FOR ADVERTISING PURPOSES.**